

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification 6 :

C09D 11/00

A1

(11) International Publication Number:

WO 96/17025

(43) International Publication Date:

6 June 1996 (06.06.96)

(21) International Application Number:

PCT/EP94/04005

(22) International Filing Date:

1 December 1994 (01.12.94)

(71) Applicant (for all designated States except US): ECKART-WERKE STANDARD BRONZEPULVER-WERKE CARL ECKART GMBH & CO. [DE/DE]; Kaiserstrasse 30, D-90763 Fürth (DE).

(72) Inventor; and

(75) Inventor/Applicant (for US only): CROWHURST, Oliver [US/US]; Apartment No. 5, 2863 Mayfield Road, Cleveland Heights, OH 44118 (US).

(74) Agent: PÖHLAU, Claus; Louis, Pöhlau, Lohrentz & Segeth, P.O. Box 30 55, D-90014 Nürnberg (DE).

(81) Designated States: AM, AU, BB, BG, BR, BY, CA, CN, CZ, EE, FI, GE, HU, JP, KE, KG, KP, KR, KZ, LK, LR, LT, LV, MD, MG, MN, MW, NO, NZ, PL, RO, RU, SD, SI, SK, TJ, TT, UA, US, UZ, VN, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG), ARIPO patent (KE, MW, SD, SZ).

Published*With international search report.*

(54) Title: CONDUCTIVE INK

(57) Abstract

The invention relates to a conductive ink material comprising a vehicle/binder system containing a metallic pigment; the inventive conductive ink material applicable in small application filmweights but presenting a high conductivity and showing a fast drying speed is characterized in that the vehicle/binder system is a water base binder system having an application viscosity of less than 1000 cps (mPa.s) preferably of less than 500 cps (mPa.s) and that the pigment is a precious metal pigment or comprises at least a precious metal coating.

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LJ	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

WO 96/17025

PCT/EP94/04005

5

10 Conductive ink

15 The invention relates to a conductive ink material comprising a vehicle/binder system containing a metallic pigment.

20 Known conductive ink materials or coatings are based on silver flakes as a metallic conductive pigment incorporated into a high viscosity vehicle/binder system having a formulation viscosity of about 10000 to 12000 cps (10000 - 12000 mPa.s). Such binder systems for example are based on vinyl or acrylic resins dissolved in organic solvents which dry by evaporation. Other known binder systems for example are based on epoxy or polyester acrylate systems comprised of 100 % of solids, which systems dry by UV-radiation curing.

30 However applying known conductive inks with the above viscosity to a substrate material requires high application filmweights in order to achieve a desired conductivity property. This is caused by the fact that due to the high viscosity of known vehicle/binder systems leafing of conductive pigment flakes is impeded thereby requiring a higher amount of conductive pigment.

WO 96/17025

PCT/EP94/04005

2

In order to dry or cure high filmweight surface coatings more energy is needed and also a long exposure to heat and/or UV-radiation is required.

5

The coating or printing procedures using screen printing processes (flatbed or rotary), both of which use high application filmweights, are relatively slow compared to conventional liquid ink processes because of the length of time the ink must remain exposed to drying units. There is however the possibility to use reel to reel screen presses with multi oven/UV driers which increase running speed but are still slow compared to liquid ink processes, i.e. flexo or gravure printing processes.

15

It is therefore an object of the present invention to propose a conductive ink material applicable in small application filmweights but presenting a high conductivity and showing a fast drying speed.

20

A conductive ink material according to the invention is characterized in that the vehicle/binder system is a water base binder system having an application viscosity of less than 1000 cps (mPa.s) preferably of less than 500 most preferably of less than 300 cps (mPa.s) and that the pigment is a precious metal pigment or comprises at least a precious metal coating. A water base binder system has a much lower application viscosity than the binder systems used with known conductive ink materials thereby promoting leafing of the metallic pigment resulting in greater alignment of conductive pigment at the surface of an ink film applied to a substrate material. Since metallic pigment flakes can orientate themselves parallel to the surface in a compact interlocking position conductivity of

30

WO 96/17025

PCT/EP94/04005

3

the ink film is considerably increased. The use of precious metal pigment additionally increases the conductivity of the ink film.

5 Within the scope of the invention there are also conductive ink materials having a formulation viscosity of more than 1000 cps prior to printing which by adding water can be decreased to fall within the above application viscosity range.

10

The conductive pigment's more random orientation throughout the ink film necessitates a higher film thickness when a known high viscosity vehicle/binder system is used. The more random orientation in these known types of ink are caused first of all by the high viscosity impeding movability and thus leafing of the metallic pigment. The lower surface tensions of the above mentioned organic solvents reduce the ability of the conductive pigment to align and orientate at the surface. The higher film thickness required in connection with known conductive ink materials means a larger distance for the conductive pigment to travel or to leaf to the surface which also results in bad surface orientation and a low conductivity.

15

20

25 The conductive ink material according to the invention not only presents a much lower application viscosity but additionally a higher surface tension due to the highly polar bonds of the water base binder system therewith promoting alignment of metallic pigment at the surface resulting in high conductivity. Accordingly lower application filmweights are needed to obtain a desired conductivity. Thus running speeds of coating or printing procedures are increased since the time an ink film must remain exposed to drying units is reduced. Use of the

30

WO 96/17025

PCT/EP94/04005

4

conductive ink material according to the invention also allows to use liquid ink processes such as flexo or gravure printing processes and other low filmweight coating processes. Accordingly it is now e.g. possible to use a
5 conductive ink printed on a plastic film as part of a mechanism that acts as a voltage or charge tester which currently is required in connection with batteries. Also the packaging for batteries can be printed by gravure process because of the high conductivity efficiency and
10 fast drying speed of conductive ink material. But also in the security and electrical circuit industry liquid ink printing processes should present an advantageous alternative to electrically depositing metals on substrate materials since electro-deposition is extremely expensive
15 and much slower compared with highspeed printing processes.

A preferred water base binder system contains about 20 to 50% preferably 30 to 40 % per weight of a solid binder substance and a viscosity of preferably less than 300 cps
20 (mPa.s), most preferably 20 to 200 cps (mPa.s). Preferably a water base colloidal dispersion of aliphatic polyester and/or polyurethane is used. A water base colloidal dispersion of an aliphatic polyester-polyurethane is obtainable as ALBERDINGK V_j - U 610 W from ALBERDINGK BOLEY
25 GMBH, Uerdingen, Germany, the type of dispersion being anionic and having about 9.5 % per weight of N-Methyl-2-pyrrolidon. However other aliphatic urethanes, acrylics or water base polymers can be used depending on the substrate to be printed or coated. As an example for an acrylic
30 binder system Zinpol 146 available from ZINCHEM, INC., Somerset, N.J, USA, should be noted comprising about 35 % per weight of an acrylic resin and about 61.8 % per weight of water and additionally 3.2 % per weight of dimethylethanolamine.

WO 96/17025

PCT/EP94/04005

5

Although the shape of the metallic pigment particles is not restrained to one predetermined profile, it is preferred to use metallic flakes in order to promote interlocking surface orientation. Mostly preferred, however, are "Lamella" shaped metallic flake pigments, which preferably are silver flakes. However, silver coated copper or other precious metals giving similar conductive properties can also be used. The precious metal pigment preferably has been treated with fatty acids, or compounds of fatty acids like fatty alcohols, preferably with stearic acid. However, palmitic acid should also be suited. The flakes have preferably low particle size compared with known conductive ink materials which has been determined according to the Cilas-method:

15

d ₁₀	0.5 - 3.5	microns
d ₅₀	1.0 - 10.5	microns
d ₉₀	6.0 - 21.0	microns

20 That means about 10% of the metallic pigment have a particle size of less than 3.5 microns, 50% of the metallic pigment has a particle size of less than 10.5 microns and 90% of the metallic pigment has a particle size of less than 21.0 microns.

25

Mostly preferred the particle size is:

d ₁₀	0.5 - 1.0	microns
d ₅₀	1.0 - 3.5	microns
30 d ₉₀	6.5 - 10.0	microns

The low particle size has been found to considerably improve the conductive properties of the ink film.

WO 96/17025

PCT/EP94/04005

6

Adding a modified hydrocarbon surfactant composition available from Rit-Chem Co., Inc. of Pleasantville, N.Y., USA, under the tradename ZEROFOME NS-31F into the water base vehicle/binder system reduces or prevents foam generation when preparing the ink material.

In order to incorporate a high percentage of silver flake pigment into a low viscosity binder system it is preferred to add a wetting agent to the conductive ink material. A preferred formulation of the conductive ink material according to the invention comprises 2,4,7,9-tetramethyl-5decyn-4,7-diol (75% in ethylene glycol) (available as Surfynol 104 H) and/or modified nonylphenoxypoly(ethyleneoxy)ethanol which is available from RHONE-POULENC, Cranbury, New Jersey, USA, under the domestic tradename IGEPAL CTA 639 W SURFACTANT and under the export tradename ANTAROX CTA-639 W SURFACTANT as a wetting agent.

A preferred formulation of the inventive conductive ink material comprises 15 to 45 % per weight of a water base binder system, 0.0 to 6.5 % per weight of a wetting agent, 20 to 80 % per weight of a metallic pigment and 0 to 20 % per weight of water. The conductive ink material preferably comprises 0.1 to 3.5 % per weight of 2,4,7,9-tetramethyl-5decyn-4,7-diol (75 % in ethylene glycol). Another preferable formulation of the conductive ink material comprises 0.1 to 3.0 % per weight of modified nonylphenoxypoly(ethyleneoxy)ethanol.

However, a mostly preferred formulation of the conductive ink according to the invention is characterized by:

- 31.7 % of a water base colloidal dispersion of aliphatic polyester/polyurethane

WO 96/17025

PCT/EP94/04005

7

- 0.5 % of a modified hydrocarbon surfactant composition
 - 57 % silver flake (silver 95 %, stearic acid 5%, e.g.
5 "Alcan Silver Flake 750")
 - 0.7 % 2,4,7,9-tetramethyl-5decyn-4,7-diol (75% in
ethylene glycol)
 - 10 - 1.8 % of modified nonylphenoxypoly(ethyleneoxy)ethanol
 - 8.3 % water
- 15 Another preferred formulation comprises as water base
vehicle binder system the dispersion Zinpol 146 or U 610 W
which have already been identified.
- 20 A method for preparing conductive ink according to the
invention consists in separately preparing a vehicle
component and a pasteous component comprising the metallic
pigment. Firstly the vehicle component is weighed into a
suitable vessel for water base ink coating manufacture. A
cavitation head type mixer is then preferably used to mix
the defoamer, which preferably is 2,4,7,9 tetramethyl-
25 5decyn-4,7-diol (75 % in ethylene glycol), which is added
to the vehicle component while mixing slowly.
- 30 In a separate vessel a wetting aid, preferably modified
nonylphenoxypoly(ethyleneoxy)ethanol is blended with the
water component according to the above given formulation to
form a gel. This is preferably done on the similar mixing
equipment. Also modified
nonylphenoxypoly(ethyleneoxy)ethanol is added.

WO 96/17025

PCT/EP94/04005

8

5 The gel so obtained is then added to the conductive pigment, which is pre-weighed in a drum of suitable size. The gel comprised of wetting aids and water is poured on top of the pigment and the drum is sealed. The volume of pigment and gel should occupy 50 - 75 % of the drum. The drum is then rotated on a drum roller for about 20 minutes or until the substance forms a homogenous paste.

10 The paste containing the metallic pigment is then added to the original vessel containing the vehicle component while agitating slowly preferably using the cavitation head type mixer. To prevent air entrapment once the paste has been added a vacuum sealed vessel may be used.

WO 96/17025

PCT/EP94/04005

9

5

C l a i m s

10

1. Conductive ink material comprising a vehicle/binder system containing a metallic pigment, characterized in that the vehicle/binder system is a water base binder system having an application viscosity of less than 1000 cps (mPa.s) preferably of less than 500 cps (mPa.s) and that the pigment is a precious metal pigment or comprises at least a precious metal coating.

20

2. Conductive ink material according to claim 1, characterized by a water base binder system comprising 30 to 40 % solids.

25

3. Conductive ink material according to claim 1 or 2, characterized by a water base colloidal dispersion of an aliphatic polyester/polyurethane.

30

4. Conductive ink material according to anyone of the preceeding claims, characterized by

WO 96/17025

PCT/EP94/04005

10

a water base binder system comprising acrylics or other polymers.

5. Conductive ink material according to anyone of the
5 preceeding claims,
c h a r a c t e r i z e d i n t h a t
the metallic pigment comprises metallic flakes
treated with fatty acid, or fatty acid components
like fatty alcohols, preferably with stearic acid.
10
6. Conductive ink material according to anyone of the
preceeding claims,
c h a r a c t e r i z e d i n t h a t
the size of the metallic pigment flakes according to
15 the Cilas-method is determined by
- | | | |
|-----------------|------------|---------|
| d ₁₀ | 0.5 - 3.5 | microns |
| d ₅₀ | 1.0 - 10.5 | microns |
| d ₉₀ | 6.0 - 21.0 | microns |
- 20 preferably by
- | | | |
|-----------------|------------|---------|
| d ₁₀ | 0.5 - 1.0 | microns |
| d ₅₀ | 1.0 - 3.5 | microns |
| d ₉₀ | 6.5 - 10.0 | microns |
- 25
7. Conductive ink material according to anyone of the
preceeding claims, additionally comprising a modified
hydrocarbon surfactant composition.
- 30 8. Conductive ink material according to anyone of the
preceeding claims, additionally comprising a wetting
agent which preferably contains 2,4,7,9-tetramethyl-
5decyn-4,7-diol (75% in ethylene glycol) and/or a
modified nonylphenoxypoly(ethyleneoxy)ethanol.

WO 96/17025

PCT/EP94/04005

11

9. Conductive ink material according to anyone of the
preceeding claims comprising:
15 to 45 % per weight of a water base binder system,
5 0.0 to 6.5 % per weight of a wetting agent
20 to 80 % per weight of a metallic pigment
0 to 20 % per weight of water
10. Conductive ink material according to claim 7, 8 or 9,
10 comprising
0.1 to 3.0 % per weight modified
nonylphenoxypoly(ethyleneoxy)ethanol.

INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 94/04005

A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 C09D11/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 C09D

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP,A,0 230 303 (B.F. GOODRICH) 29 July 1987 see page 3, line 4 - page 5, line 51; claims 1,5,13 ---	1
A	EP,A,0 462 720 (FORD) 27 December 1991 see page 3, line 31 - page 4, line 9; claim 1 ---	1
A	FR,A,2 508 922 (RCA) 7 January 1983 see page 2, line 20 - page 5, line 2; claims 1,6; examples -----	1

☐ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"A" document member of the same patent family

Date of the actual completion of the international search

9 August 1995

Date of mailing of the international search report

17. 08. 95

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+ 31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+ 31-70) 340-3016

Authorized officer

Bourgonje, A

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/EP 94/04005

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP-A-0230303	29-07-87	US-A- 4715989	29-12-87
		CA-A- 1294386	14-01-92
		DE-A- 3779141	25-06-92
		JP-A- 63006069	12-01-88
		US-A- 4774270	27-09-88
		US-A- 4826631	02-05-89
		US-A- 4950423	21-08-90

EP-A-0462720	27-12-91	US-A- 5091003	25-02-92
		CA-A- 2039590	16-12-91
		DE-D- 69107521	30-03-95
		DE-T- 69107521	14-06-95

FR-A-2508922	07-01-83	CA-A- 1173644	04-09-84
		DE-A- 3224573	20-01-83
		GB-A, B 2107302	27-04-83
		JP-B- 1053907	16-11-89
		JP-C- 1567806	10-07-90
		JP-A- 58015576	28-01-83
		US-A- 4415624	15-11-83
